



# ReboundHG

## Water Based Gym & Wood Floor Finish

### WHAT IS REBOUND HG?

REBOUND HG is a 31% self crosslinking, water based wood floor finish. REBOUND HG was designed to be a performance off set to solvent and water borne urethane finishes. Made with a patented silanol-silane polymer, the crosslinking takes place while drying. Not for use on new unfinished wood. Meets all ASTM standards for slip, detergent, and soil resistance.

### BENEFITS:

- Water Based
- Easily Repairable
- One package, no two part mixing
- 1-2 Hour recoat time (under normal conditions)
- Low Odor
- No messy screening
- Only 24 Hour gym downtime

Available Packages	
2634-55	55 Gallon Plastic Drum
2634-30	30 Gallon Plastic Drum
2634-5	5 Gallon Plastic Pail
2634-4	4 Gallon Case

### DIRECTIONS FOR USE:

Before using, make sure that the desired surface is cool to prevent early evaporation. Read MSDS and test in a small inconspicuous area.

1. Prepare Floor: Note: This finish is not designed for application to bare wood floors. Use only on previously sealed surfaces. Scrub and recoat: Dust mop floor and remove all chewing gum and labels. Using and automatic scrubber, Wet Screen floor using a 4 ounce per gallon dilution of Waterless Gym floor cleaner and a 120 grit screen. Black pads may be used instead of 120 grit screens if it has been determined that they sufficiently roughen the floor. Rinse the floor using and Automatic and Waterless gym floor cleaner until all residues have been removed.

Note: Test previously coated floor in an inconspicuous area before recoating to determine compatibility with existing finish. Apply 2 or 3 coats of finish. See finish application instructions below.

2. Apply Finish: Stir gently before using. Apply at a rate of 800-1000 square feet per gallon. Use a weighted T-Bar applicator with a clean applicator head. Apply thin, even coats with the grain of the wood. Allow a dry time of at least 1 hour between coats. Humid conditions will necessitate longer dry time. After the first coat has dried, apply a second coat. It may be necessary to screen the first coat if grain raising has occurred or it has dried longer than 6 hours. If so, screen the floor with a previously used 120 grit screen or black pad. Always vacuum and tack thoroughly after screening. Note: Do not pour unused finish back into original container. For best results, use product within 1 year of purchase date.

3. Maintain Daily: Dust mop at least daily, or more as required, to keep floor dust and dirt free. Damp mop spills, salt residue, etc. with diluted Waterless Gym Floor Cleaner and a thoroughly wrung mop.

4. Maintain Weekly: If soil conditions are heavy, auto-scrub weekly with red pads and a 2 ounce per gallon dilution of Gym Floor Cleaner.

5. Restoration: Dust mop floor. Auto-scrub with red pads with a 2-4 ounce per gallon dilution of Clean & Shine. Then dry burnish with Aqua pad. Make sure to use proper protective clothing when applying this or any chemical.

professional grade detergents & solutions